



## CERTIFICATE OF ANALYSIS

<b>PROJECT ID:</b>	<b>GS260108</b>
<b>COMMODITY:</b>	Gypsum
<b>DATE SUBMITTED:</b>	12 January 2026
<b>CLIENT DETAILS:</b>	Gypsum Supplies, 70 Kalannie-Kulja Road, Kalannie WA 6468
<b>YOUR REFERENCE:</b>	1370E

### ANALYSIS – BULK SAMPLE

Parameter	Units	Result
Loss on Drying @40°C	% w/w	0.2
Calcium	% w/w	22.9
Sulphur	% w/w	18.3
Gypsum	% w/w	98

Loss on drying analysis is representative of residual moisture content upon sample receipt, dried at 40 deg C until constant weight. Subsequent analysis performed on dry weight basis in accordance with VGB-M 701. Calcium analysis performed in accordance with VGB-M 701 2.4 complexometric method, validated against Certified Reference Material NSI QCI-145, D1022. Sulphur is determined as SO<sub>4</sub>-S by ion chromatography, validated against Certified Reference Material NSI QCI-041, D1023. Measurement uncertainty is established at +/- 1% of the result. Analysis performed in duplicate with coefficient of variation of 0.6%. Batch QC sample recovery at 100%.

Regards,

Mario Horvat *MRACI CChem*

27 January 2026